

PFINDER 871

WET DEVELOPER

FOR PENETRANT TESTING solvent based

PFINDER KG

Rudolf-Diesel-Strasse 14 71032 Böblingen/Germany + 49 (0) 7031-2701-999 ndt@pfinder.de www.pfinder-ndt.com

Version 4 / 01.03.2017

DESCRIPTION

PFINDER 871 is a solvent-based wet developer for penetrant testing. It is suitable for colour contrast and fluorescent penetrant testing.

PFINDER 871 can be wiped off from the surface or easily removed with water after testing.

PFINDER 871 is qualified for penetrant testing at temperatures between -20°C to +70°C (temperature of work part) according to EN ISO 3452-5 and EN ISO 3452-6.

Developer form d + e according EN ISO 3452-1.

APPLICATION

The capability of the penetrant system should be checked regularly by means of own reference pieces or e.g. reference test block 2 according EN ISO 3452-3.

Process description according DIN EN ISO 3452-1 see www.pfinder-ndt.com.

Before use shake spray can thoroughly until mixing balls can be heard.





GREEN ALTING WIND LINE OF THE PROPERTY OF T

YOUR GREEN NDT BENEFITS

Aerosol spray can with minimized carbon footprint



YOUR HANDLING + COST SAVING BENEFITS

- Very good developing properties
- Quick-drying
- Low consumption due to high opacity
- Easily removable with water



APPROVALS & CONFORMITIES

The product conforms to the following specifications / is suitable for use according to:

EN ISO 3452-2, ASTM E165, ASME V Art.6, RCC-M, PMUC.

Low content of sulfur and halogens according to EN ISO 3452-2.

Please respect the relevant rules and specifications for your application.

PACKAGES IN STOCK / STORAGE CONDITIONS

500-mL-spray can (for 360° application), 10-L-canister.

These packages are on stock and instantly available. Other packages on demand.

Storage between +5°C and +45°C. Shake well or stirr before use!

1 years Spray cans: 3 years

SHELF-LIFE

TECHNICAL PROPERTIES

 Density/20°C*
 DIN EN ISO 12185
 870 kg/m³

 Flash point*
 ASTM D 93
 <15°C</td>

 Productivity
 500ml Spray can
 up to 3m²

*Data of products packaged in aerosol spray cans might differ.